

Deutsch: **Technisches Datenblatt Sili-Rex 250**  
technische Qualität, 50° Shore A

Härte (Shore A)	50 ±5 Shore A
Farbe:	transparent
Dichte :	1,15 ±0,03 g/cm <sup>3</sup>
Temperaturbereich:	180° C 250° C auf Anfrage
Ölbeständigkeit:	-
Ozonbeständigkeit:	-
Röntgenbeständigkeit:	-
Witterungsbeständigkeit:	-
Reißfestigkeit:	10,4 N / mm <sup>2</sup>
Reißdehnung:	480 %
Zulassungen:	FDA 177.2600 auf Anfrage
Bemerkungen:	ggf. andere Farben möglich

Jederzeitige Änderungen vorbehalten.

Alle in diesem technischen Datenblatt erhaltenen Angaben stellen Richtwerte dar, welche sich als langjährige Durchschnittswerte erprobt haben.

english: **technical data sheet Sili-Rex 250**  
technical quality, 50° shore A

hardness (shore A) DIN 53505:	50 ±5 shore A
colour:	transparent
density (g/cm <sup>3</sup> ):	1,15 ±0,03 g/cm <sup>3</sup>
working temperature range:	180° C 250° C on demand
oil resistance:	-
ozone resistance:	-
x-ray resistance:	-
weather resistance:	-
tensile strength:	10,4 N / mm <sup>2</sup>
elongation:	480 %
permissions:	FDA 177.2600 on demand
remarks:	other colour possible

Subject to alteration without prior notice.

All mentioned properties contained in this technical data sheet are guiding values representing longterm experience average.

Rexio GmbH & Co. KG    Tel:04331/1480880    Fax: 04331/849048

Internet: [www.rexio.de](http://www.rexio.de)