

Deutsch: **Technisches Datenblatt Sili-Rex 250**
technische Qualität, 30° Shore A

Härte (Shore A)	33 ±5 Shore A
Farbe:	opaque
Dichte :	1,12 ±0,03 g/cm ³
Temperaturbereich:	180° C 250° C auf Anfrage
Ölbeständigkeit:	-
Ozonbeständigkeit:	-
Röntgenbeständigkeit:	-
Witterungsbeständigkeit:	-
Reißfestigkeit:	6,5 N / mm ²
Reißdehnung:	590 %
Zulassungen:	FDA 177.2600 auf Anfrage
Bemerkungen:	ggf. andere Farben möglich

Jederzeitige Änderungen vorbehalten.

Alle in diesem technischen Datenblatt erhaltenen Angaben stellen Richtwerte dar, welche sich als langjährige Durchschnittswerte erprobt haben.

english: **technical data sheet Sili-Rex 250**
technical quality, 30° shore A

hardness (shore A) DIN 53505:	33 ±5 shore A
colour:	opak
density (g/cm ³):	1,12 ±0,03 g/cm ³
working temperature range:	180° C 250° C on demand
oil resistance:	-
ozone resistance:	-
x-ray resistance:	-
weather resistance:	-
tensile strength:	6,5 N / mm ²
elongation:	590 %
permissions:	FDA 177.2600 on demand
remarks:	other colour possible

Subject to alteration without prior notice.

All mentioned properties contained in this technical data sheet are guiding values representing longterm experience average.

Rexio GmbH & Co. KG Tel:04331/1480880 Fax: 04331/849048

Internet: www.rexio.de